



### EPOPLEX<sup>®</sup> LS65 - Viscosity (cP)

Temperature	Hardener	White	Yellow
70°F/21°C	18300	18400	14400
75°F/24°C	12300	9340	6930
80°F/27°C	8210	5940	5150
85°F/29°C	5960	4630	3670
90°F/32°C	4710	3500	3100
95°F/35°C	3380	2530	2360
100°F/38°C	2560	1890	1740
105°F/41°C	1780	1520	1220
110°F/43°C	1510	1260	1060
115°F/46°C	1190	990	815
120°F/49°C	895	790	670
125°F/52°C	690	670	545
130°F/54°C	505	575	475