



SAFE-T-GRIP®

PRODUCT DATA

PRODUCT DESCRIPTION

Safe-T-Grip® is a two-component, 100% solids epoxy hybrid/amine cured polymer designed for use with aggregate as a tough, durable, skid resistant, high friction bonded overlay. Safe-T-Grip® is a system comprised of Safe-T-Grip® liquid and the custom color aggregate manufactured by Epoplex. Safe-T-Grip® liquid is a two-component, 100% solids epoxy hybrid/amine cured polymer formulated to provide a simple volumetric mixing ratio of two volumes of Component A (epoxy hybrid) to one volume of Component B (amine). Safe-T-Grip® is designed for use with custom color aggregates, granite and/or Bauxite.

USES, APPLICATIONS

Safe-T-Grip® may be applied to concrete, asphalt, wood and metal surfaces as a long-lasting thin overlay to provide a skid resistant high friction surface in wet and dry weather conditions. Epoplex Safe-T-Grip® aggregate is available in a variety of colors. Uses include ramps, inter-sections, specialty lanes, school zones, cross walks, etc. Safe-T-Grip® is not recommended for use over polymeric or magnesium phosphate patching materials.

PRODUCT ADVANTAGES

- 100% solids chemistry
- Hybrid epoxy chemistry maintains flexibility in cold and after aging
- Long-term high friction characteristics
- Excellent bond strength assures good adhesion to the substrate
- Special formulation chemistry for faster set at a wide range of temperatures
- Specified aggregate provides and maintains excellent skid resistance
- Low viscosity and 2:1 mix ratio for easy application

PACKAGING

Component A: Epoxy Hybrid Resin

Component B: Amine

Both components are available in 5 gallon pails, 55 gallon drums and 250 gallon totes.

PHYSICAL CHARACTERISTICS

Percent Solids	100%
Viscosity - Epoxy Hybrid Resin	800 cP
Viscosity - Amine Resin	2000 cP (ASTM D-2196)
Gel Time @ 77°F/25°C	20 minutes (ASTM D-2471)
Cure Time @ 77°F/25°C2 hours
Adhesion	> 300 psi (100% concrete failure) (ASTM D-7234)
Hardness, Shore D	75 (ASTM D-2240)
Tensile Strength	4200 psi (ASTM D-638)
Elongation	60% (ASTM D-638)
Water Absorption	0.24% @ 24 hour (ASTM D-570)
Coverage:	
Liquid Binder	0.36 gallons/sq. yd. (25 sq ft/gallon), minimum
Aggregate	22-24 lb/square yard
Compressive Strength (Mortar) (ASTM C-579)	After 3 hours - 2100 psi After 24 hours - 6500 psi After 7 days - 8700 psi
Cold Flexibility	Pass (California Test #419)
Skid Resistance (Mortar)	Granite - 80 (ASTM E-274) Bauxite - 84

Note: All properties are tested at 7 days unless otherwise noted.

STORAGE CONDITIONS

Store both components of Safe-T-Grip® in a dry area. Avoid excessive heat and do not freeze. The shelf life is two years in the original unopened container.

IMPORTANT:

Epoplex believes the information contained here to be true and accurate. Information contained here is for evaluation only. Epoplex makes no warranty, expressed or implied, based on this literature. We further reserve the right to modify and change products or literature at any time.

© 2017 Epoplex

03/17

EPOPLEX



1000 East Park Avenue, Maple Shade, NJ 08052 • 856.667.8399 • FAX 856.779.2963 • Toll Free 800.822.6920