



EPOPLEX[®] LS90 - Viscosity (cP)

Temperature	Hardener	White	Yellow
70°F/21°C	11800	7100	8630
75°F/24°C	10500	4880	6090
80°F/27°C	8310	3700	4570
85°F/29°C	6930	2930	3750
90°F/32°C	5180	2290	2810
95°F/35°C	3990	1770	2240
100°F/38°C	3020	1290	1820
105°F/41°C	2310	1020	1520
110°F/43°C	1890	825	1400
115°F/46°C	1580	665	1190
120°F/49°C	1300	555	1050
125°F/52°C	1050	475	950
130°F/54°C	930	400	885