



EPOPLEX[®] MA50 - Viscosity (cP)

Temperature	White A	Black B
77°F/25°C	44200	50900
80°F/27°C	36300	36800
85°F/29°C	21400	29300
90°F/32°C	11200	18400
95°F/35°C	7440	14300
100°F/38°C	4760	9510
105°F/41°C	3830	6500
110°F/43°C	3270	5520
115°F/46°C	2610	3900
120°F/49°C	1930	2900