


EPOPLEX



LS65qs *Viscosity vs. Temperature*

1000 East Park Avenue • Maple Shade, NJ 08052 • 856.667.8399 • FAX: 856.779.2963

EPOPLEX[®] LS65qs - Viscosity (cP)

Temperature	Hardener	White	Yellow
75°F/24°C	7380	7650	6410
85°F/29°C	4380	4720	4570
105°F/41°C	2540	3760	3220
120°F/49°C	1140	2490	1610
130°F/54°C	440	1690	1220